

Mr. Allen Robison
Refrigeration Parts Solution
PO Box 1903
S San Francisco, CA 94083-1087

Transmittal #: PR98668-51261
Date: December 2, 1998

TRANSMITTAL OF TEST RESULTS

EQUIPMENT USED: Unitherm™ Model:

1054	1091	1101	1121	1161	special	Dilatometer
QL-10	QL-11	2021	2101	<u>2031</u>	special	<u>Thermal Conductivity Meter</u>

CALIBRATION:

Using: NIST traceable NIST certified in-house working reference

DATA:

Listed below, for one test performed on one sample.
Sample's designation: vacuum insulation panel.

<u>Temperature</u>	<u>Thermal Conductivity</u>
24.9 °C	$5.087 \cdot 10^{-3} \text{ W/(m}\cdot\text{K)}$

COMMENTS:

The test was performed according to the specifications of the ASTM C518 Test Method. The estimated accuracy of the test is $\pm 3\%$.

Submitted by:

Daniela Apostolescu

Daniela Apostolescu
Laboratory Director